

**POLYfill PPC GF5020 PB**

PP-GF20

Polykemi AB

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>5</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield strain	<b>6</b>	%	ISO 527
Flexural modulus, 23°C	<b>3000</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Burning behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.6</b>	mm	-
Glow Wire Ignition Temperature (GWIT)	<b>750</b>	°C	IEC 60695-2-13
GWIT - thickness tested (1)	<b>2</b>	mm	-
<b>Other properties</b>			
Density	<b>1050</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Features**

Chemically Coupled Reinforcement

**Delivery form**

Granules

**Regional Availability**

Europe, Asia Pacific