

RamOfin PPH302G4GN56-1

PP-GF20

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
Other Standards^{S1}			
Molding shrinkage, parallel	0.4	%	Producer Method

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	4550	MPa	ISO 527
Tensile Strength	65	MPa	ISO 527
Strain at break	2.8	%	ISO 527
Izod notched impact strength, +23°C	5.7	kJ/m ²	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	1030	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.1	%	-
Mold temperature	30 - 70	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	200 - 230	°C	-
Zone 2	200 - 230	°C	-
Zone 3	200 - 250	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather

Features

Homopolymer

Certifications

RoHS compliant

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa