

Volaprint PC/ABS
(PC+ABS)

Volaprint 3 de-store

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	54	MPa	ISO 527
Yield strain	4.4	%	ISO 527

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, B	120	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10

Other properties	Value	Unit	Test Standard
Density	1130	kg/m ³	ISO 1183

Characteristics

Processing

Additive Manufacturing

Delivery form

Monofilament, Black

Features

Creep Resistance

Chemical Resistance

Grease Resistance, Oil Resistance

Regional Availability

Europe