

VYTEEN PC/ABS 8515 BK

(PC+ABS)

Lavergne

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	260	°C	-
Load	3.8	kg	-
Mold Shrinkage, MD	0.007	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.008	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	55	MPa	ASTM D 638
Elongation at Break	50	%	ASTM D 638
Flexural Modulus	2500	MPa	ASTM D 790
Flexural Strength	100	MPa	ASTM D 790
Izod Impact notched, 1/8 in	550	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1160	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Black

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America