

Witcom PC/ABS-AS-S-LM

(PC+ABS)

Wittenburg B.V.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	48	MPa	ISO 527
Strain at break	100	%	ISO 527
Flexural modulus, 23°C	1000	MPa	ISO 178
Flexural strength	43	MPa	ISO 178
Izod impact strength, +23°C	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	60	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	95	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	-

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1E9	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1140	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	250 - 280	°C	-
Mold temperature	50 - 80	°C	-
Back pressure	0 - 1	MPa	-

Characteristics**Processing**

Injection Molding

Features

Laser Markable

Special Characteristics

Anti-static

Regional Availability

Europe