

Product Texts

Polypropylene, copolymer, 30% glass fiber reinforced, chemically coupled

Flammability @3.2mm nom. HB -
 thickn.
 Flammability at thickness h (1.5 HB UL recognition (h)
 mm)

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	6200	MPa	ISO 527
^[C] Stress at break	68	MPa	ISO 527
^[C] Strain at break	3.5	%	ISO 527
^[C] Charpy impact strength, +23°C	80	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	20	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	138	°C	ISO 75-1/-2
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1120	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Regional Availability

Europe, Asia Pacific, Near East/Africa

Features

Chemically Coupled Reinforcement, Copolymer