

POLYfill PPC GF15030 PD1 VT2

PP-GF30

Polykemi AB

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Strength	70	MPa	ISO 527
Strain at break	4	%	ISO 527
Flexural modulus, 23°C	5000	MPa	ISO 178
Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	140	°C	ISO 75-1/-2
Vicat softening temperature, B	120	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Glow Wire Ignition Temperature (GWIT)	750	°C	IEC 60695-2-13
GWIT - thickness tested (1)	2	mm	-
Other properties			
Density	1120	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Features

Chemically Coupled Reinforcement

Delivery form

Granules

Regional Availability

Europe, Asia Pacific

Special Characteristics

Heat stabilized or stable to heat