

**RamOfin PPC8001G6NT**

PP-GF30

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	1.3	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Other Standards<sup>[S]</sup></b>			
Molding shrinkage, parallel	0.5	%	Producer Method

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	5250	MPa	ISO 527
Tensile Strength	58	MPa	ISO 527
Strain at break	7.3	%	ISO 527
Izod notched impact strength, +23°C	32	kJ/m <sup>2</sup>	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	1110	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.1	%	-
Mold temperature	30 - 70	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	190 - 225	°C	-
Zone 2	190 - 225	°C	-
Zone 3	190 - 245	°C	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Natural Color

**Special Characteristics**

High impact or impact modified

**Features**

Copolymer

**Certifications**

RoHS compliant

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa