

**RamOfin PPH310G6NT**

PP-GF30

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
-------------------------------------	-------	------	---------------

**Other Standards<sup>S1</sup>**

Molding shrinkage, parallel	0.2	%	Producer Method
-----------------------------	-----	---	-----------------

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
-----------------------	-------	------	---------------

**ISO Data**

Tensile Modulus	6500	MPa	ISO 527
Tensile Strength	88	MPa	ISO 527
Strain at break	3.5	%	ISO 527
Izod notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 180/1A

Other properties	Value	Unit	Test Standard
------------------	-------	------	---------------

Density	1120	kg/m <sup>3</sup>	ISO 1183
---------	------	-------------------	----------

Processing Recommendation Injection Molding	Value	Unit	Test Standard
---	-------	------	---------------

Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.1	%	-
Mold temperature	30 - 70	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	200 - 230	°C	-
Zone 2	200 - 230	°C	-
Zone 3	200 - 250	°C	-

**Characteristics****Processing**

Injection Molding

**Features**

Homopolymer

**Delivery form**

Natural Color

**Certifications**

RoHS compliant

**Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa