

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	23	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Molding shrinkage, normal	1.3	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	5000	MPa	ISO 527
Tensile Strength	75	MPa	ISO 527
Flexural modulus, 23°C	4200	MPa	ISO 178
Charpy impact strength, +23°C	48	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	145	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	125	°C	ISO 75-1/-2
Vicat softening temperature, B	145	°C	ISO 306
<b>Other properties</b>			
Density	1110	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Injection Molding

### Delivery form

Natural Color

### Features

Copolymer

### Applications

General Purpose

### Regional Availability

Europe