

Product Texts

Polypropylene, homopolymer. 31% glass fiber reinforced, chemically bonded, high flow, high heat stabilisation.

Flammability @3.2mm nom. HB
thickn. -

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	7000	MPa	ISO 527
^[C] Stress at break	95	MPa	ISO 527
^[C] Strain at break	3	%	ISO 527
^[C] Charpy impact strength, +23°C	48	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	11.5	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	148	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1140	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Features

Chemically Coupled Reinforcement, Homopolymer

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa