

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	4	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength	118	MPa	ASTM D 638
Flexural Modulus	8000	MPa	ASTM D 790
Flexural Strength	170	MPa	ASTM D 790
Izod Impact notched, 1/8 in	134	J/m	ASTM D 256
Thermal properties			
ASTM Data			
Melting Temperature	165	°C	ASTM D 3418
Other properties			
ASTM Data			
Density	1200	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
ASTM Data			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2	h	-
Melt temperature	190 - 230	°C	-
Mold temperature	60 - 80	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Black

Features

Chemically Coupled Reinforcement, Homopolymer

Regional Availability

North America, Europe, South and Central America