

**RamOfin PPH203G50NT**

PP-GF50

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	1.6	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	11500	MPa	ISO 527
Tensile Strength	110	MPa	ISO 527
Strain at break	2.1	%	ISO 527
Izod notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 180/1A
<b>Other properties</b>			
Density	1350	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Extrusion</b>			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.1	%	-
Mold temperature	30 - 70	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	200 - 230	°C	-
Zone 2	200 - 230	°C	-
Zone 3	200 - 250	°C	-

**Characteristics****Processing**

Other Extrusion

**Features**

Homopolymer

**Delivery form**

Natural Color

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa