

RamOfin PPH3001G50BK11

PP-GF50

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	0.9	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Other Standards^[S]			
Molding shrinkage, parallel	0.2	%	Producer Method

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	11100	MPa	ISO 527
Tensile Strength	100	MPa	ISO 527
Strain at break	2.5	%	ISO 527
Izod notched impact strength, +23°C	13.5	kJ/m ²	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	1330	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.1	%	-
Mold temperature	30 - 70	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	200 - 230	°C	-
Zone 2	200 - 230	°C	-
Zone 3	200 - 250	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Black

Special Characteristics

U.V. stabilized or stable to weather

Features

Homopolymer

Certifications

RoHS compliant

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa