

**CELSTRAN® CFR-TP PP GF60-13**

PP-GF60

Celanese

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>173</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	<b>-10</b>	°C	ISO 11357-1/-2

[C]: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>1490</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS