

Product Texts

Flammability @3.2mm nom. HB
thickn.

Mechanical properties**ISO Data**

	Value	Unit	Test Standard
[C] Tensile Modulus	7100	MPa	ISO 527
[C] Charpy impact strength, +23°C	35	kJ/m ²	ISO 179/1eU

[C]: CAMPUS

Thermal properties**ISO Data**

	Value	Unit	Test Standard
[C] Temp. of deflection under load, 1.80 MPa	151	°C	ISO 75-1/-2
[C] Vicat softening temperature, B	138	°C	ISO 306

[C]: CAMPUS

Other properties

	Value	Unit	Test Standard
[C] Density	1130	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Regional Availability**

North America, South and Central America