

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at break	83	MPa	ISO 527
^[C] Strain at break	3.5	%	ISO 527
^[C] Charpy impact strength, +23°C	57	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	14	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	153	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1130	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, South and Central America