

**Polytron® P30B11**

PP-GLF30

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	7000	MPa	ISO 527
Tensile Strength	110	MPa	ISO 527
Strain at break	2.2	%	ISO 527
Flexural modulus, 23°C	6700	MPa	ISO 178
Flexural strength	155	MPa	ISO 178
Charpy impact strength, +23°C	50	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	18	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	168	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	155	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	158	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-

Other properties	Value	Unit	Test Standard
Density	1120	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Mold temperature	50 - 70	°C	-
Zone 1	230 - 250	°C	-
Zone 2	230 - 250	°C	-
Zone 3	230 - 250	°C	-

**Characteristics****Processing**

Injection Molding

**Certifications**

RoHS compliant

**Delivery form**

Pellets, Black

**Applications**

Automotive

**Features**

Chemically Coupled Reinforcement, Long fiber reinforced

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa