

**QR Resin QR-10120HF-GY25618**  
(PC+ASA)

LyondellBasell Industries

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>40</b>	g/10min	ASTM D 1238
Temperature	<b>260</b>	°C	-
Load	<b>5</b>	kg	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>58.6</b>	MPa	ASTM D 638
Flexural Modulus	<b>2340</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>270</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>138</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>132</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1170</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>121</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Melt temperature	<b>304 - 327</b>	°C	-
Mold temperature	<b>82 - 116</b>	°C	-
Zone 1	<b>282 - 304</b>	°C	-
Zone 2	<b>293 - 316</b>	°C	-
Zone 3	<b>304 - 327</b>	°C	-
Nozzle temperature	<b>299 - 321</b>	°C	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

High impact or impact modified, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

**Regional Availability**

North America