

ITIPLEN IC M15 C15

PP-K15

I.T.I. Poland Sp z o.o.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Flexural modulus, 23°C	1400	MPa	ISO 178

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Density	1000	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Features

Copolymer