

**RESLEN PPC1 K15 NT 1A0000EX**

PP-K15

Polimarky Spółka Jawna

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>1.8</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>1600</b>	MPa	ISO 527
Strain at break	<b>6</b>	%	ISO 527
Charpy impact strength, +23°C	<b>12</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<b>Other properties</b>			
Density	<b>1010</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Delivery form**

Natural Color

**Regional Availability**

Europe