

**ISPLEN® PC470 AS**

PP-K40

Repsol YPF S.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>13.5</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
Molding shrinkage, parallel	<b>1.1</b>	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Flexural modulus, 23°C	<b>2600</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>1.5</b>	kJ/m <sup>2</sup>	ISO 179/1eU

Other properties	Value	Unit	Test Standard
Density	<b>1240</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Special Characteristics**

Anti-static, High impact or impact modified

**Features**

Low Warpage, Homopolymer

**Regional Availability**

North America, Europe, South and Central America, Near East/Africa