

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	13.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.1	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2100	MPa	ISO 527
Yield stress	19	MPa	ISO 527
Yield strain	2.6	%	ISO 527
Flexural modulus, 23°C	2250	MPa	ISO 178
Charpy impact strength, +23°C	45	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	2	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	50	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	3	kJ/m ²	ISO 180/1A
Izod notched impact strength	2.5	kJ/m ²	ISO 180/1A
Temperature	0	°C	-
Shore D hardness	70	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	75	°C	ISO 75-1/-2
Vicat softening temperature, A	150	°C	ISO 306
Vicat softening temperature, B	93	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1240	kg/m ³	ISO 1183

Characteristics

Special Characteristics

Anti-static, High impact or impact modified, U.V. stabilized or stable to weather

Features

Low Warpage, Copolymer

Regional Availability

North America, Europe, South and Central America, Near East/Africa