

ITIPLEN IC M20 C50

PP-K50

I.T.I. Poland Sp z o.o.

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ISO Data | | | |
| Melt flow index, MFI | 20 | g/10min | ISO 1133 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ISO Data | | | |
| Flexural modulus, 23°C | 2200 | MPa | ISO 178 |

| Thermal properties | Value | Unit | Test Standard |
|-------------------------------|--------------|-------------|----------------------|
| ISO Data | | | |
| Melting temperature, 10°C/min | 165 | °C | ISO 11357-1/-3 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1330 | kg/m ³ | ISO 1183 |

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Features

Copolymer