

UPM ForMi EXP 20

PP-L20

UPM

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1800	MPa	ISO 527
Tensile Strength	33	MPa	ISO 527
Strain at break	10	%	ISO 527
Charpy impact strength, +23°C	45	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	8.8	kJ/m ²	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	990	kg/m ³	ISO 1183

Characteristics**Processing**

Other Extrusion

Certifications

Contains renewable resources

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa