

## Polywood Cell 30 PP 48 A2 12

PP-L30

Grade is obsolete.

Advanced Compounding GmbH & Co. KG

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	1600	MPa	ISO 527
Tensile Strength	22	MPa	ISO 527
Strain at break	9.3	%	ISO 527
Flexural modulus, 23°C	1700	MPa	ISO 178
Charpy impact strength, +23°C	39	kJ/m <sup>2</sup>	ISO 179/1eU
<b>Other properties</b>			
Density	1150	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Injection Molding

#### Certifications

Contains renewable resources

#### Delivery form

Pellets

#### Applications

Automotive

#### Special Characteristics

High impact or impact modified

#### Regional Availability

Europe