

Product Texts

Polypropylene copolymer, 10% mineral filled, heat stabilized

Flammability @3.2mm nom. HB -
thickn.
Flammability @1.6mm nom. HB -
thickn.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
[C] Charpy impact strength, +23°C	80	kJ/m ²	ISO 179/1eU
[C] Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
[C] Temp. of deflection under load, 0.45 MPa	112	°C	ISO 75-1/-2
[C] Vicat softening temperature, B	78	°C	ISO 306
[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
[C] Density	970	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Copolymer

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe, Asia Pacific, Near East/Africa