

NPC-PP50HS

PP-NF50

CKT-Ökoplast GmbH

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2360	MPa	ISO 527
Tensile Strength	20	MPa	ISO 527
Charpy impact strength, +23°C	7.75	kJ/m ²	ISO 179/1eU

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Mold temperature	20 - 70	°C	-

Characteristics**Processing**

Injection Molding

Certifications

Contains renewable resources

Delivery form

Pellets, Brown

Regional Availability

Europe