

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	22	MPa	ISO 527
Flexural modulus, 23°C	2000	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	25	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	2.5	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	54	°C	ISO 75-1/-2
Vicat softening temperature, A	136	°C	ISO 306
<b>Other properties</b>			
Density	1050	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

High impact or impact modified, U.V. stabilized or stable to weather

**Features**

Non Blooming, Scratch Resistant, Copolymer

**Certifications**

Recycled Resin Content

**Applications**

Automotive

**Regional Availability**

Europe