

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	7	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2800	MPa	ISO 527
Yield stress	30	MPa	ISO 527
Yield strain	6	%	ISO 527
Flexural modulus, 23°C	2700	MPa	ISO 178
Charpy impact strength, +23°C	40	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	2	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	119	°C	ISO 75-1/-2
Vicat softening temperature, A	152	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1030	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2	h	-
Processing humidity	≤0.07	%	-
Melt temperature	220 - 240	°C	-
Mold temperature	10 - 50	°C	-
Zone 1	190 - 230	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Natural Color

Special Characteristics

High impact or impact modified

Features

Thermal Stability

Regional Availability

Europe