

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	19	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	17	MPa	ISO 527
Flexural modulus, 23°C	1700	MPa	ISO 178
Izod notched impact strength, +23°C	45	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	48	°C	ISO 75-1/-2
Vicat softening temperature, B	45	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ISO 1183

Characteristics

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Features

Scratch Resistant, Copolymer

Certifications

RoHS compliant

Regional Availability

North America, Europe, Asia Pacific, South and Central America