

Polimaxx 2311NCX TA4

PP-T20

IRPC

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	27.9	MPa	ASTM D 638
Elongation at Break	34	%	ASTM D 638
Flexural Modulus	2649	MPa	ASTM D 790
Rockwell Hardness	R 97	-	ASTM D 785
Izod Impact notched, 1/8 in	46.2	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	138	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 85	°C	-
Pre-drying - Time	2 - 3	h	-
Melt temperature	190 - 240	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Features

Copolymer

Applications

Automotive, Electrical and Electronical

Regional Availability

Europe, Asia Pacific