

PPC T20-100

PP-T20

Polymer Technologies Services Inc

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	15	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength	22.1	MPa	ASTM D 638
Flexural Modulus	2068	MPa	ASTM D 790
Izod Impact notched, 1/8 in	69.4	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	132	°C	ASTM D 648
DTUL @ 264 psi	76.7	°C	ASTM D 648
Other properties			
Density	1050	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Features

Scratch Resistant

Delivery form

Pellets, Natural Color

Regional Availability

North America