

Karilen-P H 5060 TS

PP-T60

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Other properties	Value	Unit	Test Standard
Density	1520	kg/m ³	ISO 1183

Characteristics**Delivery form**

Natural Color

Features

Homopolymer

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa