

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	13790	MPa	ASTM D 638
Tensile Strength	82.7	MPa	ASTM D 638
Flexural Modulus	13790	MPa	ASTM D 790
Flexural Strength	103	MPa	ASTM D 790
Izod Impact notched, 1/8 in	26.7	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	2570	kg/m ³	ASTM D 792
Moisture Content	0.05	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	107	°C	-
Pre-drying - Time	4 - 6	h	-
Melt temperature	302 - 329	°C	-
Mold temperature	135 - 163	°C	-
Injection pressure	68.9 - 124	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific