

Tecomid® NT40 NL MB

PPA

Eurotec Mühendislik Plastikleri

| Mechanical properties | Value | Unit | Test Standard |
|-------------------------------------|--------------|-------------------|----------------------|
| ISO Data | | | |
| Tensile Modulus | 2750 | MPa | ISO 527 |
| Yield stress | 80 | MPa | ISO 527 |
| Strain at break | 10 | % | ISO 527 |
| Izod notched impact strength, +23°C | 20 | kJ/m ² | ISO 180/1A |
| Izod notched impact strength | 18 | kJ/m ² | ISO 180/1A |
| Temperature | -30 | °C | - |

| Thermal properties | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ISO Data | | | |
| Melting temperature, 10°C/min | 315 | °C | ISO 11357-1/-3 |
| Temp. of deflection under load, 1.80 MPa | 115 | °C | ISO 75-1/-2 |
| Burning behav. at 1.5 mm nom. thickn. | HB | class | IEC 60695-11-10 |
| Thickness tested | 1.6 | mm | - |
| Burning behav. at thickness h | HB | class | IEC 60695-11-10 |
| Thickness tested | 0.8 | mm | - |

| Electrical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ISO Data | | | |
| Volume resistivity | 1E13 | Ohm*m | IEC 62631-3-1 |
| Surface resistivity | 1E13 | Ohm | IEC 62631-3-2 |
| Comparative tracking index | 600 | - | IEC 60112 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Humidity absorption | 2.2 | % | Sim. to ISO 62 |
| Density | 1150 | kg/m ³ | ISO 1183 |
| Moisture Content | 0.2 | % | - |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|--|------------------|-------------|----------------------|
| Pre-drying - Temperature | 120 | °C | - |
| Pre-drying - Time | 4 | h | - |
| Melt temperature | 320 - 330 | °C | - |
| Mold temperature | 70 - 90 | °C | - |
| Feed temperature | 60 - 80 | °C | - |
| Holding pressure | 40 - 80 | MPa | - |

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Regional Availability

Europe