

**Starflam UF0033**

PPA-GF

Eurostar Engineering Plastics

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Stress at break	<b>125</b>	MPa	ISO 527
Flexural modulus, 23°C	<b>9900</b>	MPa	ISO 178
Izod impact strength, +23°C	<b>20</b>	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	<b>3</b>	kJ/m <sup>2</sup>	ISO 180/1A

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>200</b>	°C	ISO 75-1/-2
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Thickness tested	<b>1.6</b>	mm	-

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Comparative tracking index	<b>600</b>	-	IEC 60112

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1650</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Regional Availability**

Europe

**Special Characteristics**

Flame retardant