

THERMEC N 4340R35H

PPA-GF35

DOMO Engineering Plastics

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	11500	MPa	ISO 527
Stress at break	180	MPa	ISO 527
Strain at break	2	%	ISO 527
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	310	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	285	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1

Other properties	Value	Unit	Test Standard
Density	1430	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific