

Kalix® 3850 WH 000

PPA-GF50

Grade is obsolete.

Syensqo

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0	%	ISO 294-4, 2577
Molding shrinkage, normal	0.3	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	17900	MPa	ISO 527
Yield stress	260	MPa	ISO 527
Strain at break	2.6	%	ISO 527
Flexural modulus, 23°C	17700	MPa	ISO 178
Izod impact strength, +23°C	87	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	17	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	145	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1550	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, White

Special Characteristics

Platable, High impact or impact modified

Features

Amorphous, Low Warpage

Certifications

Contains renewable resources

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific