

Denyl HT 6010

PPA-GF60

VAMP TECH SPA

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0005	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.003	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Izod impact strength, +23°C	50	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	10	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	23000	MPa	ASTM D 638
Tensile Strength at Yield	250	MPa	ASTM D 638
Elongation at Break	1.6	%	ASTM D 638
Thermal properties			
ASTM Data			
DTUL @ 264 psi	280	°C	ASTM D 648
Electrical properties			
ISO Data			
Comparative tracking index	600	-	IEC 60112
ASTM Data			
Surface Resistivity	1E12	Ohm	ASTM D 257
Other properties			
Density	1730	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	90	°C	-
Pre-drying - Time	3	h	-
Melt temperature	330	°C	-
Mold temperature	140	°C	-

Characteristics**Processing**

Injection Molding

Chemical Resistance

General Chemical Resistance

Special Characteristics

Flame retardant, Heat stabilized or stable to heat

Regional Availability

Europe