

RTP 4011 A

PPA-GF60

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0015	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	20680	MPa	ASTM D 638
Tensile Strength	221	MPa	ASTM D 638
Flexural Modulus	20680	MPa	ASTM D 790
Flexural Strength	331	MPa	ASTM D 790
Izod Impact notched, 1/8 in	107	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1750	kg/m ³	ASTM D 792
Moisture Content	0.1	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	107	°C	-
Pre-drying - Time	4 - 6	h	-
Melt temperature	329 - 343	°C	-
Mold temperature	65.6 - 163	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific