

Product Texts

LNP LUBRICOMP DL004 compound is based on Polycarbonate (PC) resin containing 20% PTFE. Added features of this grade include: Wear Resistant.

UL Yellow Card Link [E45329-101344454](https://www.ul.com/yellow-card/E45329-101344454)

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2100	MPa	ISO 527
Yield stress	47	MPa	ISO 527
Yield strain	5.3	%	ISO 527
Flexural modulus	2100	MPa	ISO 178
Izod notched impact strength, +23°C, 4mm	17	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	127	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	139	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	79	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	79	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	3.0	mm	-

Other properties	Value	Unit	Test Standard
Density	1320	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	300 - 315	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	295 - 305	°C	-
Zone 2	305 - 315	°C	-
Zone 3	310 - 320	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe