

Product Texts

LNP LUBRICOMP DP003 compound is based on Polycarbonate (PC) resin containing 15% PTFE/silicone. Added features of this grade include: Wear Resistant.

UL Yellow Card Link [E207780-101343863](https://www.ulprospector.com/usa/Products/Plastics/PC+PTFE/207780-101343863)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	0.95	mm/mm	ASTM D 955
Mold Shrinkage, TD	1.1	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2000	MPa	ISO 527
Yield stress	49	MPa	ISO 527
Yield strain	5.8	%	ISO 527
Stress at break	41	MPa	ISO 527
Strain at break	41.2	%	ISO 527
Flexural modulus	1840	MPa	ISO 178
Flexural strength	75	MPa	ISO 178
Izod impact strength, +23°C, 4mm	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	25	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	2230	MPa	ASTM D 638
Tensile Strength at Yield	48	MPa	ASTM D 638
Tensile Strength at Break	42	MPa	ASTM D 638
Elongation at Yield	5.6	%	ASTM D 638
Elongation at Break	35.1	%	ASTM D 638
Flexural Modulus	1890	MPa	ASTM D 790
Flexural Strength	75	MPa	ASTM D 790
Izod Impact notched, 1/8 in	283	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	N	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	128	°C	ISO 75-1/-2
Burning behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
ASTM Data			
DTUL @ 264 psi	127	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Humidity absorption	0.19	%	Sim. to ISO 62
Density	1260	kg/m ³	ISO 1183
Water Absorption, 24hr	0.1	%	ASTM D 570
Density	1260	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	300 - 315	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	295 - 305	°C	-
Zone 2	305 - 315	°C	-
Zone 3	310 - 320	°C	-

LNP™ LUBRICOMP™ Compound DP003 - Asia

(PC+PTFE)

Saudi Basic Industries Corporation (SABIC)

Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific