

LubriOne™ PC-000/5T-2S BK002

(PC+PTFE)

Avient Corporation

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|---------------|-------------|----------------------|
| ASTM Data | | | |
| Mold Shrinkage, MD | 0.0065 | mm/mm | ASTM D 955 |

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Strength | 55 | MPa | ASTM D 638 |
| Flexural Modulus | 2200 | MPa | ASTM D 790 |
| Flexural Strength | 80 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 450 | J/m | ASTM D 256 |

| Thermal properties | Value | Unit | Test Standard |
|---------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| UL 94 Flame rating | HB | - | UL 94 |
| Thickness tested | 3.2 | mm | - |
| DTUL @ 264 psi | 125 | °C | ASTM D 648 |

| Electrical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Surface Resistivity | 1E15 | Ohm | ASTM D 257 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1210 | kg/m ³ | ASTM D 792 |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|--|------------------|-------------|----------------------|
| Pre-drying - Temperature | 120 - 130 | °C | - |
| Pre-drying - Time | 3 - 4 | h | - |
| Mold temperature | 90 - 110 | °C | - |
| Zone 1 | 280 - 300 | °C | - |
| Zone 2 | 280 - 300 | °C | - |
| Zone 3 | 280 - 300 | °C | - |

Characteristics**Processing**

Injection Molding

Additives

Lubricants

Delivery form

Black

Regional Availability

Asia Pacific