

LubriOne™ PC-000/10T NC008

(PC+PTFE)

Avient Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0065	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	55	MPa	ASTM D 638
Flexural Modulus	2300	MPa	ASTM D 790
Flexural Strength	90	MPa	ASTM D 790
Izod Impact notched, 1/8 in	200	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	3.2	mm	-
DTUL @ 264 psi	129	°C	ASTM D 648
Electrical properties			
ASTM Data			
Surface Resistivity	1E15	Ohm	ASTM D 257
Other properties			
Density	1250	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	120 - 130	°C	-
Pre-drying - Time	3 - 4	h	-
Mold temperature	90 - 110	°C	-
Zone 1	290 - 310	°C	-
Zone 2	290 - 310	°C	-
Zone 3	290 - 310	°C	-

Characteristics**Processing**

Injection Molding

Additives

Lubricants

Delivery form

Natural Color

Regional Availability

Asia Pacific