

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at break	90	MPa	ISO 527
^[C] Strain at break	1.5	%	ISO 527
^[C] Charpy impact strength, +23°C	18	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	260	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 8.00 MPa	200	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	0.02	%	Sim. to ISO 62
^[C] Density	1580	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Regional Availability

North America, Europe, South and Central America, Near East/Africa