

**S1070A10**

PPS-(GF+MD)70

Cheng Yu Plastic Company Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength	120	MPa	ASTM D 638
Flexural Strength	200	MPa	ASTM D 790
Rockwell Hardness	M 101	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	V-0	-	UL 94

Other properties	Value	Unit	Test Standard
Density	2000	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	150	°C	-
Pre-drying - Time	6	h	-
Melt temperature	300 - 350	°C	-
Mold temperature	130 - 170	°C	-

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Flame retardant, Heat stabilized or stable to heat

**Chemical Resistance**

General Chemical Resistance

**Applications**

Automotive, Chemical Process, Electrical and Electronical

**Regional Availability**

Asia Pacific