

TEDUR L 9200-1

PPS-(GF+MF)60

MOCOM Compounds GmbH & Co. KG

Product Texts

Base Polymer	Polyphenylene Sulphide
Filler/Additive System	60 % glass fibre/mineral
Special Features	high toughness
Market Segment	Automotive, various
Typical Applications	seals, various

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	17000	MPa	ISO 527
^[C] Stress at break	150	MPa	ISO 527
^[C] Strain at break	1.2	%	ISO 527
^[C] Charpy impact strength, +23°C	30	kJ/m ²	ISO 179/1eU

[C]: CAMPUS

Thermal properties

	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	275	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
^[C] Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Electrical properties

	Value	Unit	Test Standard
ISO Data			
^[C] Comparative tracking index	150	-	IEC 60112

[C]: CAMPUS

Other properties

	Value	Unit	Test Standard
^[C] Density	1900	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, Near East/Africa

Other text information**Injection molding**

Pre-Drying Conditions	in a dry air (dessiccant) dryer 130-140 °C for 2-4 h dependant on moisture content
Processing Injection Moulding	melt temperature 320-340 °C mould temperature >140 °C
Storage	dry, protected from light not above 30°C