

DIC-PPS FZ-3805-A1

PPS-(GF+MX)

DIC Trading (USA) Inc.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0025	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0077	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	19000	MPa	ASTM D 638
Tensile Strength	125	MPa	ASTM D 638
Elongation at Break	1.2	%	ASTM D 638
Compressive Strength	160	MPa	ASTM D 695
Flexural Modulus	18000	MPa	ASTM D 790
Flexural Strength	200	MPa	ASTM D 790
Rockwell Hardness	R 121	-	ASTM D 785
Izod Impact notched, 1/8 in	70	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	240	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.8	mm	-
Coefficient of Thermal Expansion, MD	18	E-6/K	ASTM D 696
DTUL @ 264 psi	265	°C	ASTM D 648
Electrical properties			
ASTM Data			
Dielectric Strength, Short Time	16	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.005	-	ASTM D 150
Dielectric Constant, 1 MHz	4	-	ASTM D 150
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Other properties			
Water Absorption, 24hr	0.02	%	ASTM D 570
Density	1930	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Black

Regional Availability

North America, Europe, Asia Pacific

Features

Low Warpage