

Ryton® R-7-120NA

PPS-(GF+MX)

Syensqo

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.004	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Tensile Strength	140	MPa	ISO 527
Strain at break	0.9	%	ISO 527
Flexural modulus, 23°C	19000	MPa	ISO 178
Izod impact strength, +23°C	15	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Strength	131	MPa	ASTM D 638
Elongation at Break	0.9	%	ASTM D 638
Compressive Strength	265	MPa	ASTM D 695
Flexural Modulus	19300	MPa	ASTM D 790
Flexural Strength	207	MPa	ASTM D 790
Rockwell Hardness	M 101	-	ASTM D 785
Izod Impact notched, 1/8 in	59	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	210	J/m	ASTM D 256
Thermal properties			
ISO Data			
Burning behav. at 1.5 mm nom. thickn. Thickness tested	V-0	class mm	IEC 60695-11-10 -
Burning behav. 5V at thickness h Thickness tested	5VA	class mm	IEC 60695-11-20 -
ASTM Data			
DTUL @ 264 psi	265	°C	ASTM D 648
Limiting Oxygen Index	61	%	ASTM D 2863
Electrical properties			
ASTM Data			
Dielectric Strength, Short Time	16	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.002	-	ASTM D 150
Dielectric Constant, 1 MHz	4.9	-	ASTM D 150
Surface Resistivity	>1E15	Ohm	ASTM D 257
Volume Resistivity	1E15	Ohm*cm	ASTM D 257
Arc Resistance	185	s	ASTM D 495
Other properties			
Water Absorption, 24hr	0.02	%	ASTM D 570
Density	1990	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa